



food processor supplies

Bunzl Food Processor
Supplies Pty Ltd
ABN: 17 000 011 441

Sydney
34-48 Cosgrove Road
Enfield NSW 2136
Locked Bag 3011
Burwood NSW 2134
Australia

Tel: +61 2 9737 2100
Fax: +61 2 9642 0229
www.bunzl.com.au

4th December 2017

SPECIFICATION SHEET

Code:	BZBPCUT460710
Description:	PAPER BAKING SILICONE 460X710MM
GSM:	44gsm
Quantity:	500 sheets per carton
Material:	Siliconised Baking Paper. Silidor is a bleached non opaque, two side silicone treated natural greaseproof paper with excellent heat stability, manufactured from virgin fibre with high chemical purity.
Dimension:	460x710 mm
Country of Origin:	Norway/Sweden
Storage Conditions:	Stored Temperature and humidity controlled to ensure that the product is stored in a controlled environment and under optimum conditions.
Regulations:	<ul style="list-style-type: none">➤ Regulation (EC) 1935/2004 on materials and articles to come into contact with food (raw materials).➤ French Decree no 2007-766 supplement 2008-1469.➤ Directive 94/62/EC on Packaging and packaging waste.
Typical end use:	An environmental friendly reusable baking paper. Also suitable for cooking and frying.

Disclaimer:

The information provided is based on the product's manufacturer and a copy of manufacturer's declaration is held on file. We have every reason to believe that the information provided is accurate.

Property	Test Method	Unit	Typical Value			
Grammage Tolerance +/- 5%	ISO 536	g/m2	39	40	41	44
Bulking Thickness	ISO 534	µm	44	46	46	49
Brightness	ISO 2470	%	72	72	72	72
Tearing Resistance • MD • CD	ISO 1974	mN	200 220	200 220	200 220	220 240
Tearing Resistance after Heating (200°C/20 min) • MD	ISO 1974	mN	140	140	140	140
Water absorptiveness, Cobb₆₀ • TS	ISO 535	g/m2	11	11	11	11

Property	Test Method	Unit	Typical Value			
Grammage Tolerance +/- 5%	ISO 536	g/m2	50	55	57	70
Bulking Thickness	ISO 534	µm	54	60	62	73
Brightness	ISO 2470	%	72	72	72	72
Tearing Resistance • MD • CD	ISO 1974	mN	230 250	240 260	240 260	290 320
Tearing Resistance after Heating (200°C/20 min) • MD	ISO 1974	mN	160	170	170	215
Water absorptiveness, Cobb₆₀ • TS	ISO 535	g/m2	11	11	11	11

Julie Butcher

Julie Butcher
Business Analyst/ Quality Assurance Manager



Disclaimer:

The information provided is based on the product's manufacturer and a copy of manufacturer's declaration is held on file. We have every reason to believe that the information provided is accurate.