

Technical Data Sheet

White Waxed Casguard

Non-Woven PP with Wax

The following options are available:

- **Pre-Cut Sheets**
 - **Width:** 100mm – 1000mm
 - **Length:** 100mm – 1000mm
- **Perforated Roll**
 - **Width:** 100mm – 1180mm
 - **Perforation:** 50mm – 1000mm
- **Non-Perforated Roll**
 - **Width:** 100mm – 1180mm

All rolls are either 90mtrs or 45mtrs in length

<u>Property</u>	<u>Test Method</u>	<u>Value</u>	<u>Unit</u>
Non-Woven PP	100mm x 100mm	0.5	Gm ±10%
Overall Weight	100mm x 100mm	2.0	Gm ±10%
Non-woven PP		25	%
Non-woven PP		200	um
Tensile Strength (MD)	ASTM D882	≥ 15	MPa
Tensile Strength (TD)	ASTM D882	≥ 15	MPa
Temperature Range		2-45	°C

* Due to variability in the wax overall material thickness cannot be determined.

**MUST BE STORED OUT OF DIRECT SUNLIGHT AND WITHIN THE STATED
TEMPERATURE RANGE**

All of the raw materials used in the making of the films/pouches are approved for food contact according to the FDA/USDA standards by the material manufacturers and comply with requirements set forth in the FDA/USDA regulations 21 CFR section 177.1520 (Polyethylene/Polypropylene), 177.1360 (EVOH), 177.1350 (EVA), 175.105 (Adhesives), 177.1500 (Polyamide), 177.1330 (Ionomer) and 177.1350, 177.1570 (EP film).

CPSS REV 2

caspak.com.au

+61 (03) 9540 4000 / sales@caspak.com.au

4-6 Sugar Gum Court, Braeside, Vic 3195, Australia / ABN: 59 875 253
895