

Pollard's Sawdust Supplies

SONSAN AUSTRALIA PTY LTD

A.B.N. 62 095 191 692

EUCALYPTUS HARDWOOD SAWDUST Technical Data Sheet

Hardwood Flour: Chemical & Physical Properties

Acidity (pH)	3.5 - 4.6
Ash Content	0.23 to 0.25 Hardgrove index
Colour	Red to Light Brown
Density	12 - 18 pounds/cubic feet
Moisture Content	4 - 6% - Dependent on relative humidity
Solubility in water	< 0.1%
Specific Gravity	0.5 - 0.8

130 YAN YEAN ROAD PLENTY•VIC • 3095
TELEPHONE: 03 9435 6167• FAX: 03 9432 0738